

TECHNICAL DATA SHEET

HDPE Extrusion granules

Physical Properties	Metric
<i>Density</i>	<u>0,955-0,961 g/cm³</u>
<i>Shape and Size</i>	<u>Regrind</u>
<i>Quality</i>	<u>Regrinded and washed HDPE bottles and canisters</u>
<i>Melt Flow</i>	<u>0.7-1.5 g/60 sec (190°C 5 kg)</u>
<i>Colour</i>	<u>Light grey/green</u>
Delivery Options	
<i>Packaging</i>	<u>Big-Bags, max 1100 kg</u>
<i>Delivery on pallets</i>	<u>1x1.2m</u>
<i>Truck</i>	<u>20-22 t per truck</u>

